

# VINYCOL 1520M2

## SOLVENT BASED CONTACT ADHESIVE FOR PVC INFLATABLES

### PRODUCT BENEFITS

- Suitable to bond PVC and PU inflatable boats
- Easy to apply
- High temperature and water resistance

### Applications

- Bonding coated PVC or PU materials (inflatable boats, strip conveyor, etc.).
- Advised to use Desmodur RFE or RC, or FIXDUR 100.

### Method of use

**Surface preparation:** Surface needs to be sanded, subsequently removed from dust and grease.

**Dosage:** The average dosage is 8% by weight but in terms of use and pretesting, different doses can be used. Vinycol 1520 M2 has high resistance to hydrolysis, and a very good heat resistance.

**Relative humidity:** A humidity below 60% is recommended during implementation.

### APPLICATION:

- Apply an adhesive film on both surfaces
- Apply the first layer and let it cure for about 10 minutes.
- Apply the second layer and let it cure for about 15 to 20 minutes.
- Check both surfaces and press strongly immediately after assembly.

- Maximum open time: 30 minutes.

Data according to laboratory tests:

Peel strength:

a) After 24h at 20°C : > 100N / 5cm

b) After 7d at 20°C : > 200N / 5cm

c) After 7d at +70°C : > 100N / 5cm

Resistance to shear creep under load (800N @80°C) : >1h

Resistance to hydrolysis by total immersion in boiling water:

### Technical data

<b>Base</b>	Polyurtehane
<b>Viscosity</b>	2600 Mpas (@20°C)
<b>Dry Content</b>	20% (20m @60°C)
<b>Density</b>	0.87 g/ml
<b>Flammability</b>	<21°C (flashpoint)
<b>Colour</b>	Opalescent
<b>Packaging</b>	10L

a) After 24h: 100% nominal

b) After 48h: 85% nominal

c) After 72h: 66% nominal

### STORAGE STABILITY

Vinycol 1520 M2 can be stored for 12 months in an unopened container in a dry and temperate place at ±18°C.

### FURTHER INFORMATION

The following publication is available on request:

- Material Safety Data Sheets (MSDS Sheet).

### BOSTIK HOTLINE

**Smart help +44 123 45 678**



#### Bostik SA

Colombes, FRANCE

Phone : +33 (0)1 55 99 90 00

Fax : +33 (0)1 55 99 90 01

[www.bostik.com](http://www.bostik.com)

#### Bostik Ltd.

Stafford, UK

Phone : +44 (0) 1785 27 27 27

Fax : +44 (0) 1785 22 26 65

[www.bostik.com](http://www.bostik.com)

#### Bostik GmbH

Borgholzhausen, Germany

Phone : +49 (0)54 25/801-0

Fax : +49 (0)54 25/801140

[www.bostik.com](http://www.bostik.com)

#### Bostik BV

's-Hertogenbosch, NL

Phone : +31 (0)7 36 244 244

Fax : +31 (0)7 36 244 344

[www.bostik.com](http://www.bostik.com)