



# ISR 70-08 AP

## SILYL MODIFIED POLYMER

TECHNICAL SHEET 14/11/2023

### KEY FEATURES

- Excellent Green strength
- Primerless adhesion
- Free from Isocyanate, Solvent and Silicone

### DESCRIPTION

Bostik ISR 70-08 AP is a high quality elastic bonding adhesive with excellent initial tack, suitable for bonding of structures in industrial applications requiring high strength.

Bostik ISR 70-08 AP has excellent resistance to UV, weather and temperature, and exhibits excellent adhesion performance on a wide variety of substrates (minimal or no pre-treatment necessary).

Bostik ISR 70-08 AP has been tested according to DIN6701-2.

### APPLICATIONS

- Window bonding and sealing
- Elastic bonding in mobility market applications, e.a. Bus & Coach, Railway, etc.

### FEATURES

- Very good UV resistance and ageing properties
- Good adhesion on many substrates without the use of a primer
- Neutral, odourless and fast curing
- Paint compatible with most industrial paint and lacquer systems, both alkyd resin- and dispersion based.

(due to the numerous different types of industrial paint a compatibility test is recommended before use, please consult with the paint supplier).

### TECHNICAL DATA

CHARACTERISTIC		VALUE
Basic material		Silyl Modified Polymer (SMP)
Curing method		Moisture
Specific gravity	[g/ml]	ca. 1.5
Skin forming time 23°C/50% R.H.	[min]	ca. 10
Curing speed after 24hrs 23°C/50% R.H.	[mm]	ca. 3
Shore A hardness		ca. 60
Volume change	[%]	ca. < 3
Electrical Volume Resistivity	[Ω·cm]	>10 <sup>11</sup>
Tensile stress (100%) ISO 37 (dumbbells)	[MPa]	ca. 2.4
Tensile stress at break ISO 37 (dumbbells)	[MPa]	ca. 2.9
Elongation at break ISO 37 (dumbbells)	[%]	ca. 200
E-Modulus (10%) ISO 37 (dumbbells)	[MPa]	ca. 5.5
Shear stress ISO 4587	[MPa]	ca. 2.3
Glass transition (Tg)	[°C]	ca. -59
Temperature resistance	[°C]	-40 to +110*
Application temperature	[°C]	+ 5 to +40
UV and weather resistance		Excellent
Colours (standard)		White, Black
Packaging		290ml cartridges 600ml sausages 20L & 200L drums

\* = 10 Cycles of 7 hours at 100°C followed by 17 hours at 23°C/50%RH.

## ADHESION

Bostik ISR 70-08 AP adheres well without primer on most clean, dry, dust and grease free substrates. Due to the wide variety of substrates available Bostik recommends adhesion testing prior to use.

No adhesion will be obtained on untreated polyethylene, polypropylene and Teflon.

Where, due to great thermal or physical loads, high adhesion demands are required, the use of Bostik Prep CS or Prep M is recommended, especially under wet conditions. Prep CS and Prep M degrease and prepare the surface of the substrate for bonding in one single step.

On plain, untreated wooden surfaces and porous substrates, Bostik Prep P is recommended to prepare the surface for bonding. For more details on Prep CS, Prep M and Prep P consult the concerned Technical Data Sheet.

## METHOD OF USE

Bostik ISR 70-08 AP can easily be extruded with a hand or air pressure applicator at temperatures between +5°C and +35°C. In bonding applications, the substrates need to be assembled within 15 minutes (at 23°C/50% R.H.) of applying ISR 70-08 AP. A minimum adhesive thickness of 2 mm is recommended. Bostik ISR 70-08 AP should be tooled off or smoothed within 15 minutes (at 23°C/50% R.H.) using a spatula or putty knife, occasionally moistened with a watery soap solution (avoid soap containing limonene as these can cause discoloration of the sealant). Avoid soap solution penetrating between joint sides and adhesive, as this will cause loss of adhesion. Cleaning tools or removing uncured residue of ISR 70-08 AP can be done with a clean colourless cloth, wetted with Bostik Liquid 1.

## STORAGE

ISR 70-08 AP can be stored for up to 18 months in cartridge and 12 months in sausage, in original, unopened container in a dry place at temperatures between +5°C and +30°C.

## FURTHER INFORMATION

The following publication is available on request:

- Material Safety Data Sheets (MSDS).

## SMART HELP

Please contact your local representative



### DISCLAIMER

Bostik offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations.

The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein.

**Bostik S.A.**  
Colombes, France  
Phone : +33 (0)1 49 00 90 00  
[www.bostik.fr](http://www.bostik.fr)

**Bostik Ltd.**  
Stafford, UK  
Phone : +44 (0) 1785 27 27 27  
[www.bostik.co.uk](http://www.bostik.co.uk)

**Bostik GmbH**  
Borgholzhausen, Germany  
Phone : +49 (0)54 25/801-0  
[www.bostik.de](http://www.bostik.de)

**Bostik B.V.**  
Oosterhout, The Netherlands  
Phone : +31 (0)162 491 000  
[www.bostik.nl](http://www.bostik.nl)

All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.